

V100WG2



WHITE



PRODUCT DESCRIPTION:

Printable film composed of a 50- μ m cast PVC, which is coated with a pressure-sensitive grey acrylic adhesive. For solvent, eco-solvent, latex and UV inkjet printing. Glossy surface finish.

FILM FEATURES:

• Thickness	(Indicative value) 50 μm	
• Total thickness	(Indicative value) 230 μm	
• Total weight	(Average values) 245 g/m²	Method HEXGSM001
• Tensile strength	(Average values) min. 20 N/25 mm	Method HEXNFX41021
• Elongation at break	(Average values) min. 70 %	Method HEXNFX41021
• Shrinkage 168 hours at 70 °C (158 °F)	(Average values) < 0.3 mm	Method HEXRET001
• Opacity	(Average values) > 98 %	Method HEXOPA001

LINER:

- Silicone-coated PE paper 145 g/m² with light grey «THE CAST by HEXIS» print.
- Stable under hygrometric variations

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

• Peel strength test at 180° ; Measurement support glass		
after 20 minutes of application	(Average values) 13 N/25 mm	Method HEXFTM001
after 24 hours of application	(Average values) 15 N/25 mm	Method HEXFTM001
• Initial tack	(Average values) 14 N/25 mm	Method HEXFTM009
• Release	(Average values) 0.2 N/25 mm	Method HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

ADHESIVE:


- Grey, solvent-based acrylic adhesive.
- Immediate and permanent adhesion.

PRINTING GUIDE:

- Touch-dry after less than 10 minutes depending on the printer used.
- Optimal drying time for the inks before laminating or further processing is 48 hours minimum.

USER'S INSTRUCTIONS:

- +10 °C (+50 °F) for flat surfaces and with a minimum of +15 °C (+59 °F) for riveted surfaces.
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)



- Adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.
- In the case of an already painted substrate, apply to undamaged original paintwork only. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

- The surface finish of your printings may be modified/improved/protected by applying one of these laminates: PC500, PC190 or PC30.
- For more information on the application method of the V100WG2 film, please refer to its Application Guide available under the «Professionals» heading, in the «Digital printing media» category on our website www.hexis-graphics.com.

STORAGE:



Storage period before use
1 year



Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage
with relative humidity between 30 % and 70 %



Storage method before use
in its unopened original packaging

DURABILITY: CENTRAL EUROPEAN CLIMATE

- Vertical outdoor exposure:
Unprinted: 10 years,
printed and laminated:
- PC500: 5 years.
- PC30 and PC190: 4 years.
Printed: 2 years.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site www.hexis-graphics.com.

CERTIFICATION:

Fire-smoke classification



Fire-smoke classification standard
EN 13501-1

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.